

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Borg Manufacturing Pty Ltd  
2 Wella Way  
Somersby NSW 2250

**Test Number :** 20-002979  
**Issue Date :** 16/07/2020  
**Print Date :** 16/07/2020

**Sample Description** Clients Ref : "Structaflor GP 19mm"  
Raw Particleboard  
Nominal Thickness : 19mm

### ASTM C518-2017

### Steady-State Thermal Transmission Properties by Means of the Heat Flow Apparatus

Test Date	15/07/2020	
Test Apparatus	Lasercomp Fox 314	
Sample Orientation	Horizontal	
Heat Flow Direction	Up	
Mean Test Temperature	23 °C	
Temperature Differential	20 °C	
Average Thermal Gradient	1035.2 K/m	
Estimated uncertainty in results	3.1 %	
Specimen	1	2
Specimen Thickness (as received)	19	19 mm
Specimen Thickness (as tested)	19	19 mm
Specimen Density (as tested)	650	662 kg/m <sup>3</sup>
Test Duration	01:00	00:56 hrs:mins
Measured Heat Flux	122.0	121.7 W/m <sup>2</sup>
Measured Thermal Conductance	0.6100	0.6084 W/m <sup>2</sup> K
Measured Thermal Conductivity	0.1178	0.1176 W/m.K
Thermal Resistance	0.16	0.16 m <sup>2</sup> K/W

208963

44803

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Borg Manufacturing Pty Ltd  
2 Wella Way  
Somersby NSW 2250

**Test Number :** 20-002979  
**Issue Date :** 16/07/2020  
**Print Date :** 16/07/2020

The calibration of the Heat Flow Apparatus was checked immediately prior to the commencement of the test.

208963

44803

Page 2 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR